

Anderson Development Company



Compression Deflection Data (psi)

Product	Curative	Hardness	5%	10%	15%	20%	25%	Compression Modulus
7-3 APLF	MBOCA	71A	70	160	260	335	415	1740
8 APLF	MBOCA	81A	120	260	420	535	645	2840
8-3 APLF	MBOCA	85A	145	310	500	630	755	3480
8-5 APLF	MBOCA	88A	170	390	625	790	945	4625
9 APLF	MBOCA	91A	215	485	775	975	1160	5875
9-5 APLF	MBOCA	51D (95A)	290	675	1065	1370	1645	8380
7 APLM	MBOCA	70A	65	145	235	310	380	1610
8 APLM	MBOCA	81A	115	255	410	520	625	2900
9 APLM	MBOCA	91A	175	400	650	820	975	4775
5 DPLM	MBOCA	51D	250	660	1065	1360	1620	8995
6 DPLM	MBOCA	60D	1100	1850	2200	2450	2750	25000
7 DPLM	MBOCA	70D	1600	3200	3800	4200	4600	48000
2-77 AP	MBOCA	77A	90	210	345	440	540	2400
80-5 AP	MBOCA	86A	125	315	530	680	820	3920
2-90 AP	MBOCA	92A	195	480	785	1000	1200	5930
2-95 AP	MBOCA	95A/52D	285	765	1240	1595	1920	10300
2-60 DP	MBOCA	60D	520	1400	2190	2795	3340	19400
2-72 DP	MBOCA	65D	900	2080	3260	4000	4800	32000
1-75 DP	MBOCA	74D	2500	4700	5500	6000	6600	66000
80 APLF	MBOCA	81A	85	220	370	485	590	2925
85 APLF	MBOCA	86A	120	320	535	790	830	4000
90 APLF	MBOCA	89A	150	385	630	810	970	4780
93 APLF	MBOCA	94A	205	585	930	1185	1410	7565
95 APLF	MBOCA	52D (95A)	300	810	1305	1640	1985	10100
60 DPLF	MBOCA	60D	730	1760	2660	3240	3810	30000
70 DPLF	MBOCA	70D	1800	3450	4250	4900	5500	52000
75 DPLF	MBOCA	75D	2000	4800	6000	6400	6800	78000
80 DPLF	MBOCA	80D	3700	8000	10000			105000
8000 AP	MBOCA	82A	105	230	380	495	600	2515
8500 AP	MBOCA	87A	110	280	470	615	745	3435
9000 AP	MBOCA	92A	160	420	700	905	1090	5530
9500 AP	MBOCA	95A	175	580	960	1240	1490	8840
5000 DP	MBOCA	50D	350	890	1340	1650	1960	15000
6500 DP	MBOCA	65D	1200	2200	2650	3200	3700	27000
7500 DP	MBOCA	75D	2600	5000	5600	6100	6600	69000
9500 APLF	MBOCA	52D	300	825	1295	1625	1910	11600
6500 DPLF	MBOCA	65D	1400	2600	3100	3500	3900	36600
7201 DPLF	MBOCA	72D	1700	3600	4600	5500	6400	55000
7501 DPLF	MBOCA	77D	2400	5700	6800	7500	8300	88000