

Anderson Development Company



Compression Deflection Data (psi)

Product	Curative	Hardness	5%	10%	15%	25%	Compression Modulus
M 8-5 AP	Curene 45	84A	140	315	490	810	3600
BA-M 9-3 AP	Curene 45	92A	250	550	830	1270	6500
M 9-5 AP	Curene 45	95A	270	600	930	1520	6800
LQ-M 9-5 AP	Curene 45	95A	300	625	950	1400	7700
HC BA-M 9-5 AP	Curene 45	95A	330	800	1280	1800	11000
M 75 AP	Curene 45	75A	75	160	255	470	1800
M 80 AP	Curene 45	80A	TBD	TBD	TBD	TBD	TBD
M 85 AP	Curene 45	85A	130	310	490	830	3600
M 90 AP	Curene 45	90A	170	425	670	1050	5450
M 93 AP	Curene 45	92A	TBD	TBD	TBD	TBD	TBD
M 95 AP	Curene 45	95A	300	675	1000	1600	9000
M 52 DP	Curene 45	52D	470	1100	1700	2500	14000
M 60 DP	Curene 45	60D	840	1720	2350	3500	21600